

1. PRODUCT NAME

TEC® Contractor Grade Self Leveling Underlayment (567)



2. MANUFACTURER

H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451 U.S.A.
800.552.6225 Office
800.952.2368 Fax
tecspecialty.com

3. DESCRIPTION

TEC® Contractor Grade Self Leveling Underlayment is a pumpable/pourable cement based, self-leveling underlayment designed for use over a variety of substrates. The resulting smooth finished surface is ideal for the installation of all types of floor covering, including carpet, ceramic or natural stone tile, resilient, laminate flooring and wood flooring (for interior dry area use only).

Note: All surfaces must be primed with TEC® Multipurpose Primer before application of TEC® Contractor Grade Self Leveling Underlayment.

Key Features and Benefits

- Calcium aluminate technology for rapid strength development
- Superior flow properties
- Use directly over green concrete <95% RH or 15 lbs per 1,000 ft² (0.07 kg/m²) per 24 hours]
- Thickness ranges from 1/8" (1.6 mm) up to 1" (25 mm) depth in a single pour, up to 5" (12 cm) with proper aggregate
- Cures to a smooth, consistent finish
- Walkable in 4-6 hours, ceramic tile in 24 hours, finished floor coverings can be applied in 48 hours.
- Contributes to LEED® project points
- 1-year limited warranty

Packaging

50 lb. moisture-resistant bags (22.68 kg)

Product #7062093111

Coverage

Coverages shown are approximate. Actual coverage may vary based on substrate conditions. Coverage per 50 lbs. (22.68 kg) TEC® Contractor Grade Self Leveling Underlayment.

Application Depth	Approximate Coverage
1/8" (3 mm)	42-48 sq.ft. (3.9-4.5 m ²)
1/4" (6 mm)	21-24 sq.ft. (2.0-2.2 m ²)
1/2" (12 mm)	10-12 sq.ft. (0.9-1.1 m ²)
1" (25 mm)	5-6 sq. ft. (0.5-0.6 m ²)

Suitable Substrates

When properly prepared, suitable substrates include:

- Concrete
- Ceramic or quarry tile (well-bonded)
- Exterior grade plywood
- Oriented Strand Board (OSB)

Substrate Preparation

It is required that all surfaces be structurally sound and free from any contaminants that may inhibit bond, including oil, grease, dust, loose or peeling paint, sealers, floor finishes, or curing compounds, etc. Minimum tensile bond strength of 72 psi (0.5 MPa) is required. Substrate temperature should be a minimum of 43°F (6°C) during application and air temperature maintained above 50° (10°C). DO NOT cover existing building expansion or control joints. Provide control joints where specified. Create 1/8" to 1/4" (3-6 mm) wide gaps where self-leveling underlayment abuts walls, columns, and fixtures by installing a self-sticking foam weather stripping tape or damp sand (vacuum up sand after self-leveling underlayment has cured). Plug all floor openings, gaps and cracks and install termination dams to prevent any seepage. **Surfaces must be primed with TEC® Multipurpose Primer prior to installation of TEC® Contractor Grade Self Leveling Underlayment.** See Primer label for application instructions.

TEC® Contractor Grade Self Leveling Underlayment can be installed over green concrete with RH of 95% or less. For moisture sensitive floor coverings refer to the finished floor manufacturer's specifications on moisture limitations. Remediation of excessive moisture conditions must be addressed prior to the installation TEC® Contractor Grade Self Leveling Underlayment. To reduce moisture vapor emissions to an acceptable level, use TEC® LiquiDam™ Penetrating Moisture Vapor Barrier (see product data sheet for details).

TEC® Contractor Grade Self Leveling Underlayment is not recommended for use over adhesives and/or residues.

Single Layer of Exterior Grade Plywood or Oriented Strand Board (OSB) with Lath:

Wood subflooring must be securely fastened with screw type or ring shank nails and adhesive. Installations of exterior grade plywood or OSB (APA Rated Sturd-I-Floor OSB, Exposure 1 or better) require 3/4" (19 mm) single layer minimum thickness on bridged floor joists up to 24" (60 cm) on center, with a maximum deflection of 1/360 of the span. Allow a gap of 1/8" to 1/4" (3-6 mm) between sheets of plywood or OSB. Long edges of subfloor must be tongue and groove or supported by bridging between floor joists. Use suitable TEC® surface preparation products (PerfectFinish™, VersaPatch®, Fast-Set Deep Patch) to plug all floor openings, gaps and cracks and install termination dams to prevent any seepage. Prime the floor and allow it to dry to a clear film. Next, staple 1/4" (6 mm) galvanized diamond metal or plastic lath to the floor overlapping 2" (5 cm) at seams. Staple every 6" (15 cm) around the perimeter and overlaps, and every 8" (20 cm) in the field of the lath. Install TEC® Contractor Grade Self Leveling Underlayment based upon the following joist spacing in the table below:

Joint Spacing (o.c.)	Minimum SLU thickness with lath over single layer 3/4" (19 mm) tongue and groove subfloor
16" or less (40 cm or less)	3/8" (9 mm)
20" or less (50 cm or less)	1/2" (12 mm)
24" or less (60 cm or less)	5/8" (15 mm)

Storage

Store in cool, dry area away from direct sunlight. Do not store open containers.

Shelf Life

Maximum of 1 year from date of manufacture in properly stored, unopened package.

Limitations

- For interior use only.
- Do not apply when the temperature is below 50°F (10°C).
- All surfaces must be primed with TEC® Multipurpose Primer before application of underlayment.
- Not for use in conditions of hydrostatic pressure or excessive moisture [>95% RH or 15 lbs per 1,000 ft² (0.07 kg/m²) per 24 hours].
- Do not use as a wear surface.
- Do not use over non-dimensionally stable substrates, such as gypsum and vinyl.

Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered TEC® brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

4. TECHNICAL DATA

TEC® Contractor Grade Self Leveling Underlayment (567)		
Description	Test Standard	Typical Results
28 Day Compressive Strength	ASTM C109	4000 psi (27.3 MPa)
28 Day Flexural Strength	ASTM C580	700 psi (4.8 MPa)
Tensile Strength	ASTM C307	300 psi (2.1 MPa)
28 Day Shrinkage	ASTM C531 (Modified)	0.025-0.045%

Physical Properties

Description	
Physical State	Dry powder
Color	Gray
Working Time	15-20 minutes
Walkable Hardness	4-6 hours
Flooring Installation*	24 hours: tile and stone 48 hours: all other flooring
Flow (ASTM C1708)**	11"-12" (27-30 cm)
Storage	Store in cool, dry area away from direct sunlight. Do not store open containers.
Shelf Life	Maximum 1 year from date of manufacture in properly stored, unopened package.

**Flooring material installation in 24-48 hours after application is dependent on thickness, drying conditions, and type of flooring.

**Ideal flow range is based in 2" (5 cm) diameter plastic/metal pipe by 4" (10 cm) high.

5. INSTALLATION INSTRUCTIONS**Mixing**

Slowly add the entire bag of TEC® Contractor Grade Self Leveling Underlayment to a maximum of 4.5 quarts (4.3 L) of clean, cool water and mix with a high power drill (650 RPM). Avoid breathing dust and contact with eyes and skin. Mix thoroughly for two (2) to three (3) minutes. Scrape container's sides and remix to ensure a smooth, lump-free consistency. TEC® Contractor Grade Self Leveling Underlayment can also be used in most pump equipment. Please consult your TEC® representative to verify equipment compatibility. A flow test should always be performed to ensure that the mix is homogenized and free from separation.

Application

Immediately after mixing, pour TEC® Contractor Grade Self Leveling Underlayment onto the primed substrate. Spread into place with a long-handled, gauged spreader or smoother covering all high spots on the floor. Working time is approximately 15-20 minutes, depending on ambient temperature and relative humidity of air. High temperatures and low humidity will shorten working time. TEC® Contractor Grade Self Leveling Underlayment can be applied from a 1/16" up to 1" (1.6-25 mm) depth in a single application. Up to 5" (12 cm) thickness may be poured with the addition of aggregate [well-graded, washed, dry pea gravel 1/8" (3 mm) or larger].

First mix the TEC® Contractor Grade Self Leveling Underlayment as instructed. During placement add equal parts of aggregate to mixed self-leveler by volume, mix until completely coated. To ensure proper bond, all aggregate and substrate must be completely coated with the underlayment mixture. Do not use sand. For further information, please contact your TEC® representative.

Clean-up

While material is still fresh, wash tools, hands and equipment with warm soapy water.

Curing/protection

TEC® Contractor Grade Self Leveling Underlayment dries to walkable hardness in 4 to 6 hours. Tile and stone floor coverings can be installed in 24 hours and all other floor coverings can be installed in 48 hours. TEC® Contractor Grade Self Leveling Underlayment is cement-based, and all general rules of concrete work should be observed to achieve maximum results. In hot, dry or drafty conditions protect the installation to avoid fast water loss while curing. Never use forced air to accelerate the drying of TEC® self-leveling cements. For best results, always test performance of finished floor systems prior to installation.

6. AVAILABILITY

TEC® Premium Tile and Stone Installation Products are available nationwide. To locate TEC® products in your area, please contact:

Phone: 800-832-9002
Website: tecspecialty.com

7. WARRANTY

For warranty details, see your sales associate or visit tecspecialty.com.

8. MAINTENANCE

Not applicable

9. TECHNICAL SERVICES**Technical assistance**

Information is available by calling the Technical Support Hotline.

Toll Free: 800-832-9023


Fax: 630-952-1235

Technical and safety literature

To acquire technical and safety literature, please visit our website at tecspecialty.com.

10. FILING SYSTEM

Division 9



tecspecialty.com

©Copyright 2016 H.B. Fuller Construction Products Inc.

TEC®, LiquiDam™, PerfectFinish™ and VersaPatch® are trademarks of H.B. Fuller Construction Products Inc.

LEED® is a registered trademark of U.S. Green Building Council.

 **H.B. Fuller**
CONSTRUCTION PRODUCTS
H.B. Fuller Construction Products Inc.
1105 South Frontenac Street
Aurora, IL 60504-6451

DS567 R0316-1