

Hits the Spot

See Reverse for
More Information ▶



Introducing TEC® AccuColor® Plus - on target for commercial specs

TEC® AccuColor® Plus is your solution for commercial installations that need to meet the ANSI A118.7 specification. It delivers color consistent grout joints from 1/16" to 1/2" (1.6 - 12 mm) wide for both interior and exterior tile installations. AccuColor® Plus is a fast setting grout that provides stain and efflorescence resistance in most any environment and in most applications.

Advanced performance and features you can count on.





Stain resistant to most common household stains



Open to water exposure in 72 hours



Color accurate and resistant to efflorescence

Additional Features and Benefits

- Meets ANSI A118.7 specifications
- For grout joints from 1/16" to 1/2" (1.6-12 mm) wide
- Crack and shrink resistant
- Mold and mildew resistant

Packaging

25 lb. plastic bags (11.34 kg)

Colors

Available in 32 colors. Contact H.B. Fuller Construction Products Inc. ("HBF-CP") for a current color selection card.

Mixing

For best results pour water in a bucket and then add powder. In a clean mixing container, add AccuColor® Plus to clean, cool water as specified below:

Size	Water
25 lbs. (11.34 kg)	2-2.5 quarts [64-80 fl. oz.] (1.89-2.37 L)

1. Start with the low-end water range
2. Mix with a drill (350 rpm max.) and mixing paddle attachment for a minimum of 2 minutes
 - Do not add more water until material has been mixed for 2 minutes
 - After 2 minutes, if more water is needed, add water with care not to exceed recommended range
3. Allow to stake in bucket for 3-5 minutes
4. Remix with drill and mixing paddle for a minimum of 1 minute

Technical Data

Applicable Standard

When mixed with water and tested, AccuColor® Plus meets ANSI A118.7 Specifications for Ceramic Tile Grouts and Polymer-modified Cement Grout. ISO 13007: Classification CG2WAF.

Description	ANSI A118.7 Requirement	Typical Results
28 Day Compressive Strength	≥ 3000 psi (20.7 MPa)	6500 psi (44.8 MPa)
28 Day Tensile Strength	≥ 500 psi (3.4 MPa)	650 psi (4.5 MPa)
28 Day Flexural Strength	≥ 1000 psi (6.9 MPa)	1200 psi (8.3 MPa)
27 Day Linear Shrinkage	< 0.20% shrinkage	< 0.20% shrinkage
28 Day Water Absorption	< 5% absorption	< 3% absorption

Greater than: > Greater than or equal to: ≥ Less than: < Less than or equal to: ≤

Physical Properties

Description	
Physical State	Dry powder
Color	Available in 32 colors
Pot Life	1 hour
Stain Resistance	Allow to cure for 7 days to achieve maximum stain resistance.
Initial Cure [at 72°F (22°C)]	3 to 4 hours
Final Cure	21 days
Foot Traffic Rating (ASTM C627)	Residential to Extra Heavy Commercial
Storage	Store in cool, dry location. Do not store open containers.
Shelf Life	Maximum 12 months from date of manufacture in unopened package

Visit tecspecialty.com to learn more