

# **Acrylic Grout Additive**

#### 1. PRODUCT NAME

TEC® Acrylic Grout Additive (869)

#### 2. MANUFACTURER

H.B. Fuller Construction Products Inc. 1105 South Frontenac Street Aurora, IL 60504-6451 U.S.A. 800.552.6225 Office 800.832.9023 Technical Support 800.952.2368 Fax tecspecialty.com

## 3. DESCRIPTION

TEC® Acrylic Grout Additive is an acrylic latex admixture formulated for use in place of water when grouting ceramic. This additive is specifically formulated for use with any of TEC® AccuColor® portland cement grouts.

TEC® Acrylic Grout Additive makes joints less susceptible to water penetration (especially important when grouting wet areas). It also increases grout flexibility. It is required for any exterior grout application subjected to freeze/thaw conditions or any ANSI A118.7 application.

#### **Key Features and Benefits**

- · Highly water resistant
- · Increases grout flexibility
- Required for exterior grout applications subjected to freeze/thaw conditions
- Meets ANSI A118.7 specifications

#### **Packaging**

64 fl. oz. plastic jugs (1.89 L) Product #15035258 1 gallon plastic jugs (3.78 L) Product #15035256

# **Surface Preparation**

Proper preparation of the tile and joint surfaces is important and will help promote a quality installation. The joints between the tiles should be free from foreign materials, and be at least  $\frac{2}{3}$  of the thickness of the tile in depth. High ridges of adhesive, cement, or thin set should be raked out. Rubber or plastic tile spacers, if used, should be removed prior to grouting. Tiles should be held firmly in place according to manufacturer's instructions before grouting.

Due to rough surface texture or high porosity, some tiles require sealing prior to grouting. Consult the tile manufacturer's/fabricator's literature for advice regarding this point. TEC® recommends the use of grout release for protecting your tile from grout staining during installation.

#### Storage

Store in cool, dry location. Do not expose to nor store in direct sunlight. Do not store open containers.

## **Shelf Life**

Maximum of 18 months from date of manufacture in unopened package.

## Limitations

- Recommended for use as a grout additive only.
- Do not use TEC® Acrylic Grout Additive as an admixture to mortars.
- Latex-modified grout should not be applied when the temperature of the area is below 50°F (10°C) as the curing process is retarded.
- Ideal working temperature is between 50°-70°F (10°-21°C).
- Do not store open containers.
- Avoid excessive high speed mechanical mixing as air is entrained into the grout, which reduces its strength.
- Latex additives are not recommended for grouting natural stone tile.

#### **Cautions**

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered TEC® brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

## 4. TECHNICAL DATA

## **Applicable Standard**

Mixed with TEC® AccuColor® sanded floor grout and tested in accordance with ANSI A118.7 Specifications for Ceramic Tile Grouts, Latex Modified Commercial Portland Cement.

TEC® Acrylic Grout Additive (869)			
Description	ANSI Requirement	Typical Results	
28 Day Compressive Strength	> 3000 psi (20.7 MPa)	3800-4200 psi (26.2-29.0 MPa)	
28 Day Tensile Strength	> 500 psi (3.5 MPa)	500-600 psi (3.5-4.1 MPa)	
7 Day Flexural Strength	> 1000 psi (6.9 MPa)	1000-1200 psi (6.9-8.3 MPa)	
7 Day Linear Shrinkage	< 0.10% shrinkage	0.06-0.08% shrinkage	
Greater than: > Greater than or equal to: ≥ Less than: < Less than or equal to: ≤			

#### **Physical Properties**

Description		
Physical State	Acrylic emulsion	
Color	White, dries clear	
Odor	Nil	
Viscosity	Thin, liquid	
Wt. per U.S. Gallon	8.4 lbs. ± 0.1 lb.	
Wt. per Liter	1.01 kg ± 0.01 kg	
VOC	2 g/L	
Freeze/Thaw Stability	Freeze/thaw stable. If frozen, thaw and stir before using.	
Storage	Store in cool, dry location. Do not expose to nor store in direct sunlight. Do not store open containers.	
Shelf Life	Maximum 18 months from date of manufacture in unopened package	

## 5. INSTALLATION INSTRUCTIONS

#### Mixina

For best results add powder to liquid. In a clean mixing container, add unmodified grout to additive as specified below:

<b>Grout Size</b>	<b>Unsanded Grout</b>	Sanded Grout
1 lbs.	5 fl. oz.	2.25-2.5 fl. oz.
(0.454 kg)	(147.8 mL)	(66-74 mL)
9.75 lbs.	1½-1½ quarts	2 <sup>3</sup> / <sub>4</sub> -3 cups
(4.42 kg)	[40-48 fl. oz.] (1.2-1.4 L)	[22-24 fl. oz.] (600-700 mL)
25 lbs.	3½-4 quarts	1 <sup>3</sup> / <sub>4</sub> -2 quarts
(11.34 kg)	[112-128 fl. oz.] (3.3-3.78 L)	[56-64 fl. oz.] (1.65-1.89 L)
50 lbs. (22.68 kg)		3½-4 quarts [112-128 fl. oz.] (3.30-3.78 L)

Mix well. If necessary, add additional water to achieve a smooth, stiff consistency. Allow mixture to "slake" (sit in the container) for 10 minutes, then remix before using. Slaking allows the water, Portland cement and other ingredients to react properly.

## Note: Liquid latex additives are not recommended for grouting natural

**stone.** See grout container for detailed application and cleaning instructions. When grouting unglazed tiles, particularly those with rough surface texture or high porosity, presealing tile prior to grouting may be necessary.

## **Application**

Install in accordance with detailed instructions on  $\mathsf{TEC}^{\circledcirc}$  grout product packages or data sheets.

## 6. AVAILABILITY

TEC® Premium Tile and Stone Installation Products are available nationwide. To locate TEC® products in your area, please contact:

Phone: 800-832-9002 Website: tecspecialty.com

## 7. LIMITED WARRANTY

The product(s) covered by this Product Data Sheet are sold subject to a Limited Warranty and related terms. H.B. Fuller Construction Products disclaims the implied warranties of merchantability and fitness for a particular purpose and all incidental and consequential damages arising out of the sale, purchase or use of this product. For Limited Warranty details visit tecspecialty.com. To obtain a hard copy of the Limited Warranty call H.B. Fuller Construction Products at 800-832-9023 or mail a written request to the address in Section 2 of this Product Data Sheet.

## 8. MAINTENANCE

Not applicable

## 9. TECHNICAL SERVICES

## Technical and safety literature

To acquire technical and safety literature, please visit our website at tecspecialty.com.

## **10. FILING SYSTEM**

Division 9



## To learn more, visit TECspecialty.com



H.B. Fuller Construction Products Inc. | 1105 South Frontenac Street Aurora, IL 60504-6451







